## **TEST REPORT**

No.: XMIN190100111CCM

Date: Jan.22, 2019

Page: 1 of 2

CUSTOMER NAME: ENDUTEX REVESTIMENTOS TEXTEIS, S. A

ADDRESS: RUA DA BAIONA 22, 4795-784 VILARINHO S-TIRSO

Sample Name : PRINT FLOOR

Material : PVC COATED POLYESTER WOVEN FABRIC

Spec : 85% PVC AND 15 POLYESTER

Manufacturer : ENDUTEX REVESTIMENTOS TEXTEIS, S. A

Above information and sample(s) was/were submitted and confirmed by the client. SGS, however, assumes no responsibility to verify the accuracy, adequacy and completeness of the sample information provided by client.

\*\*\*\*\*\*

Test Required : Selected test(s) as requested by applicant

Date of Receipt : Jan.16, 2019
Testing Start Date : Jan.16, 2019
Testing End Date : Jan.22, 2019

Test Result(s) : For further details, please refer to the following page(s)

(Unless otherwise stated the results shown in this test report refer only to the

sample(s) tested)

\*\*\*\*\*\*\*\* To be continued\*\*\*\*\*\*\*

Signed for SGS-CSTC Standards Technical Services Co., Ltd. Xiamen Branch Testing Center

Civi Huang Authorized Signatory

# **TEST REPORT**

No.: XMIN190100111CCM

Date: Jan.22, 2019

Page: 2 of 2

Slip resistance (oil-wet ramp test)

### **Test Method:**

DIN 51130:2014-02 Testing of floor coverings - Determination of the anti-slip property - Workrooms and fields of activities with slip danger, walking method - Ramp test

## **Sample Description:**

Floor,1300mm×700mm, 1pc,see the photo(s)

### **Test Result:**


Testing direction& testing surface: see the photo(s)

Test item(s)	Test result(s)	Classification
Slip resistance (oil-wet ramp test)	Critical angle of inclination:7.8°	R9

#### Classification of oil-wet ramp test:

Classification	Angle (degrees)
R9	6°≤X≤10°
R10	10° <x≤19°< td=""></x≤19°<>
R11	19° <x≤27°< td=""></x≤27°<>
R12	27° <x≤35°< td=""></x≤35°<>
R13	>35°

## Specimen photograph(s):



SGS authenticate the photo(s) on original report only

\*\*\*\*\*\*End of report\*\*\*\*\*\*\*\*